

# TECHNICAL DATA SHEET

REVIGRÉS - Indústria Revestimentos de Grés Lda  
 Apartado 1 - 3754-001 Barrô - Agueda | Portugal  
 Tel: +351 234 660 100 | revigres@revigres.pt  
 www.revigres.com



**Ref. standard**

EN 14411: 2012 Ceramic floor and wall tiles: definitions, classification, characteristics and marking

**Product type**

Dry pressed: group Bla UGL  
 Full body porcelain tiles | edge rectified | matt surface

**Coleção**

**DI ALBA STONE RECT**

**Formats**

(30x60) 29.5x59.2x0.85 | (60x60) 59.2x59.2x0.85 | (45x90) 44.35x88.9x1.05  
 (90x90) 88.9x88.9x1.05 cm | (60x120) 59.2x118.6x0.98 cm

**Colors**

Grey, carbon



TEST METHODS	STANDARD METHOD	STANDARD VALUE	TYPICAL VALUE
Length and Width <sup>1)</sup>	ISO 10545-2	± 0.6% max.2.0 mm	± 0.1% max.± 1.0 mm
Thickness <sup>1)</sup>		± 5% max.± 0.5 mm	± 5% max.± 0.5 mm
Straightness of the edges <sup>2)</sup>		± 0.5% max.± 2.0 mm	± 0.2% max.± 0.8 mm
Orthogonality <sup>2)</sup>		± 0.5% max.± 2.0 mm	± 0.2% max.± 1.5 mm
Surface flatness <sup>2)</sup>		± 0.5% max.± 2.0 mm	± 0.3% max. ± 1.8 mm
Surface quality (% defect free)		≥ 95%	Compliant
Water absorption	ISO 10545-3	< 0.5%	< 0.05%
Bending strength	ISO 10545-4	8.5 mm	> 2000 N
		9.8   10.5 mm	> 3500 N
Rupture modulus	ISO 10545-4	> 35 N/mm <sup>2</sup>	> 45 N/mm <sup>2</sup>
Resistance to deep abrasion	ISO 10545-6	< 175 mm <sup>3</sup>	< 120 mm <sup>3</sup>
Coefficient of linear thermal expansion (with atmospheric temperature up to 100 °C)	ISO 10545-8	As indicated by producer	≤ 8,0x10 <sup>-6</sup> °C <sup>-1</sup>
Resistance to thermal shock	ISO 10545-9	Required	Resist
Resistant to frost	ISO 10545-12	Required	Resist
Resistance against acids and alkalis	ISO 10545-13	low concentrations	Class LA
		high concentrations	Class HA
Resistance to household chemicals and swimming pool water additives	ISO 10545-13	Mín. Classe B	Class A
Resistance to staining	ISO 10545-14	As indicated by producer	Class 5
Antislip resistance	DIN 51130	Max. R13	R10
	DIN 51097	Max. C	B
	ENV 12633	Max. Class 3	Class 2
	BS 7976 [#96 rubber]	Test method available	> 36
	ANSI A137-1	Test method available	≥ 0,42
Reaction to fire	EN 13823 . EN 9239-1	A1 <sub>FL</sub>	Class A1FL / Class A1

<sup>1)</sup> permissible deviation of the average value for each tile from the work size (w); <sup>2)</sup> deviation related to corresponding work sizes;

Revigres guarantees compliance with all the requirements of the EN 14411 Grupo Bla UGL standard.  
 The typical value is indicative and does not have the nature of a negotiation proposal.  
 Technical specifications are only valid for the products classified as 1st choice.  
 The use of the product must be adapted to its traffic intensity and slip resistance classification.  
 For additional information, please contact: revigres@revigres.pt.

pelo departamento qualidade  
 2024.05.22